

Dear Customer,

we have available a new version of poly flex resin, whose code is T 50 and hardener K 55.

This new edition doesn't need the oven for drying but has a short time of use, about 10 minutes mixing 100 grams of resin and 100 grams of hardener.

INSTRUCTIONS TO FOLLOW CAREFULLY FOR T50 RESIN WITH HARDENER K55, DRYING AT AMBIENT TEMPERATURE

- . Store spare cans, cartons or pallets at ambient temperature.
- . Work in an air-conditioned environment, humidity max 50%, optimal conditions also for the storage of cans to be used for the mixture.
- . Mix resin and hardener with Vacuum Poly Mix C80 **for 3 minutes.**
- . **RATIO MIX 1:1**
- . Quantity to use: max 100 gr resin + max 100 gr hardener
- . Short working time, about 10 mins.
- . Flame the labels with bubbles remover.
- . **Resin T50 can also dry at ambient temperature.**
- . Resin T50 and hardener K55 are not compatible with any other leftovers of previous supplies with different reference codes.

We suggest to do the usual tests before making the production.

Best regards,
Manicardi srl